



TECHNICAL DATA SHEET

KEIM COLOUR-CONCENTRATES

1. PRODUCT DESCRIPTION

KEIM Colour-Concentrates are highly pigmented colour products for on-site tinting of KEIM dispersion silicate paints. KEIM Colour-Concentrates can also be used directly as a weather-resistant paint and comply with DIN 18 363 Para. 2.4.1.

2. FIELD OF APPLICATION

KEIM Colour-Concentrates can be used on all mineral substrates. KEIM Colour-Concentrates is suitable for renovating old building structures as well as for new buildings thanks to its excellent product properties. A wide variety of applications are possible in combination with the precisely coordinated product components of the KEIM Granital system.

Not suitable for:

substrates with salt efflorescences; saponifiable existing substrates; horizontal and inclined surfaces exposed to weathering; plasto-elastic coatings

3. PRODUCT PROPERTIES

- economical in consumption
- non-film forming
- mineral matt
- environmentally friendly
- highly water-repellent
- highly permeable
- highly weather-resistant
- resistant against industrial emissions
- anti-fungal and anti-algae thanks to ideal moisture balance
- fire behaviour: non-flammable
- no solvents added

MATERIAL CHARACTERISTICS:

- Density: approx. 1,3 - 1.6 g/cm³
- Organic content: ≤ 5 %
- pH value: approx. 11
- Colour fastness (Fb-code pursuant to BFS Leaflet No. 26): A1

CLASSIFICATION:

- Classification according to: DIN EN 1062-1
- Classification according to VOB: Silicate emulsion paint according to DIN 18363 sec. 2.4.1
- Water vapour diffusion current density (V-value): > 2000 g/(m² · d)
- Diffusion-equivalent air layer thickness (sd-value): ≤ 0,01 m
- Diffusion-equivalent air layer thickness class: V1
- Standard Diffusion equivalent air layer thickness DIN EN ISO 7783: DIN EN ISO 7783
- Water permeability: ≤ 0,1 kg/(m²√h)

TECHNICAL DATA SHEET – KEIM COLOUR-CONCENTRATES

- Water permeability rate class: W3
- Standard Water permeability rate
DIN EN 1062-3: DIN EN 1062-3
- Gloss level at 85°: matt
- Standard Gloss level ISO 2813: ISO 2813

COLOUR SHADES:

monochrome shades 9001 to 9010 available. See KEIM Palette Exclusiv.

4. APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION:

The substrate must be dry, sound, free from chalking, clean and dust-free. Loose parts of existing coatings must be removed mechanically or by high-pressure water jetting. Defective areas must be filled and texture-matched using a suitable repair material. Any sintered layers on new renders must be removed with KEIM Fluat-10 according to instructions. New render areas (repairs) are generally to be pretreated with KEIM Fluat-10 according to the specifications in the Technical Data Sheet. Strongly absorbing surfaces must be primed with KEIM Spezial-Fixativ. Please, refer to the Technical Data Sheet of the primer regarding application and dilution. Repaired substrates and substrates with structural differences or hairline cracks require a base coat with the higher filled KEIM Granital-Grob instead of KEIM Colour-Concentrates. In case of larger cracks or strong structural differences, a primer coat with the higher filled KEIM Contact-Plus might be necessary instead of KEIM Granital-Grob.

Sound, organic, existing coatings must be precoated with KEIM Contact-Plus as bridging coat.

Old coatings that are plasto-elastic or susceptible to saponification are not suitable for coating. Old, film-forming coatings that are not sound or hinder vapour diffusion must be removed with the paint stripper KEIM Dispersionsentferner or by mechanical methods. A pretreatment with KEIM Silangrund is recommended for surfaces exposed to high moisture or weathering.

APPLICATION CONDITIONS:

Ambient and substrate temperature ≥ 5 °C during application and drying. Do not apply in direct sunlight or on sun-heated substrates. Protect surfaces from direct sun, wind and rain during and after application.

PREPARATION OF MATERIAL:

Stir up KEIM Colour-Concentrates thoroughly before application.

CONSUMPTION:

approx. 0,4 kg/m² for two coatings.

These material consumption values are guide values for smooth substrates. Exact consumption values must be determined by means of test areas.

APPLICATION:

KEIM Colour-Concentrates can be painted, rolled or sprayed (nozzle: ≥ 435 , for further information see TM on airless technology). On difficult, poorly and/or differently absorbent substrates, Special Fixative (Spezial-Fixativ) KEIM is recommended as a thinner.

Primer coat: For the primer coat, application with a roller or brush is recommended. Apply KEIM Colour-Concentrates in the normal case undiluted or depending on the absorbency of the substrate, diluted up to max. 20 % with KEIM Spezial-Fixativ.

Final coat: Apply KEIM Colour-Concentrates undiluted.

Note: Three coats are recommended in the event of very heavy use.

DRYING TIME:

Can be overcoated after 12 hours at the earliest (at 23 °C and 50% RH).

After pre-treatment with KEIM Silangrund, apply the primer coat after approx. 4 hours.

CLEANING OF TOOLS:

Clean immediately with water.

TECHNICAL DATA SHEET – KEIM COLOUR-CONCENTRATES

5. PACKAGING

Container content	Unit of measure	Quantity on pallet	Type of container
5	kg	70	bucket

6. STORAGE

max. storage time	Storage conditions
12 months	cool frost-free keep container tightly sealed.

7. DISPOSAL

For disposal information refer to section 13 of the safety data sheet.

Waste code: 08 01 12

8. SAFETY INSTRUCTIONS


Please, refer to the Material Safety Data Sheet. EU limit value for this product (Cat. A/a): 30 g/l; (Cat. A/c): 40 g/l.
This product contains: 0 - 1 g/l VOC.

9. GENERAL INFORMATION

Cover surfaces not to be treated, especially glass, ceramics and natural stone. Any splashes on surrounding surfaces or traffic areas must be rinsed off immediately with plenty of water.

Mixing with products not part of the system or other foreign additives is not permitted.

10. CERTIFICATES & QUALITY SEALS



The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release the purchaser and processor from the obligation to convince themselves of the suitability of our products for the intended application with due care, which is general practice in trade and crafts. The general rules of construction technology must be observed. We reserve the right to make modifications to improve the product or its application. This edition supersedes all earlier editions.



KEIM MINERAL PAINTS LTD
Santok Building / Deer Park Way, Donnington Wood / Telford / Shropshire TF2 7NA
Tel. +44 1952 231 250 / Fax +44 1952 231 251
www.keim.com / sales@keimpaints.co.uk